

FORTRON® 9141L4

Polyphenylene sulfide

Fortron 9141L4 is a 40% glass-reinforced PPS that has excellent heat and chemical resistance, inherently flame-retardant, high hardness and a good balance of strength and stiffness. This grade exhibits low flash and is typically used in applications with thicker walls and shorter flow lengths.

Product information

| | | |
|----------------------|------------|-----------|
| Resin Identification | PPS-GF40 | ISO 1043 |
| Part Marking Code | >PPS-GF40< | ISO 11469 |

Rheological properties

| | | |
|------------------------------------|-------------|-----------------|
| Moulding shrinkage range, parallel | 0.2 - 0.6 % | ISO 294-4, 2577 |
| Moulding shrinkage range, normal | 0.4 - 0.6 % | ISO 294-4, 2577 |

Typical mechanical properties

| | | |
|---------------------------------------|----------------------|--------------|
| Tensile modulus | 15500 MPa | ISO 527-1/-2 |
| Tensile stress at break, 5mm/min | 195 MPa | ISO 527-1/-2 |
| Tensile strain at break, 5mm/min | 1.9 % | ISO 527-1/-2 |
| Flexural modulus | 14800 MPa | ISO 178 |
| Flexural strength | 290 MPa | ISO 178 |
| Charpy impact strength, 23°C | 53 kJ/m ² | ISO 179/1eU |
| Charpy impact strength, -30°C | 53 kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 12 kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 12 kJ/m ² | ISO 179/1eA |
| Poisson's ratio | 0.33 ^[C] | |

[C]: Calculated

Thermal properties

| | | |
|---|--------|----------------|
| Melting temperature, 10°C/min | 280 °C | ISO 11357-1/-3 |
| Glass transition temperature, 10°C/min | 90 °C | ISO 11357-1/-3 |
| Temperature of deflection under load, 1.8 MPa | 270 °C | ISO 75-1/-2 |

Flammability

| | | |
|--------------------------------------|-----------|-----------------|
| Burning Behav. at 1.5mm nom. thickn. | V-0 class | IEC 60695-11-10 |
| Thickness tested | 1.5 mm | IEC 60695-11-10 |
| Burning Behav. at thickness h | V-0 class | IEC 60695-11-10 |
| Thickness tested | 0.38 mm | IEC 60695-11-10 |

Physical/Other properties

| | | |
|-----------------------|------------------------|----------------|
| Water absorption, 2mm | 0.02 % | Sim. to ISO 62 |
| Density | 1650 kg/m ³ | ISO 1183 |

Injection

| | |
|---------------------------------|---------|
| Drying Recommended | yes |
| Drying Temperature | 130 °C |
| Drying Time, Dehumidified Dryer | 2 - 4 h |
| Processing Moisture Content | ≤0.02 % |
| Melt Temperature Optimum | 330 °C |

FORTRON® 9141L4

Polyphenylene sulfide

| | |
|--------------------------|---------------|
| Min. melt temperature | 310 °C |
| Max. melt temperature | 340 °C |
| Screw tangential speed | 0.2 - 0.3 m/s |
| Mold Temperature Optimum | 150 °C |
| Min. mould temperature | 140 °C |
| Max. mould temperature | 160 °C |
| Hold pressure range | 30 - 70 MPa |
| Back pressure | 3 MPa |

Characteristics

| | |
|-------------------------|--|
| Processing | Injection Moulding |
| Delivery form | Pellets |
| Additives | Release agent |
| Special characteristics | Flame retardant, Heat stabilised or stable to heat, Chemical resistant |

Additional information

Processing Notes

Pre-Drying

FORTRON should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -30^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

The pre-drying conditions can influence the flow (melt viscosity) of the material significantly. The drying temperature can be subject of optimization for flow of the material depending on the injection molding process and the tool- or part design.

Storage

For subsequent storage the material should be stored dry in the dryer until processed (≤ 60 h).