

# FORTRON® FX55T1

## Polyphenylene sulfide

Fortron® FX55T1 is an unreinforced, impact-modified poly(phenylene sulfide) with high melt viscosity suitable for extrusion.

### Product information

Resin Identification	PPS	ISO 1043
Part Marking Code	>PPS<	ISO 11469

### Rheological properties

Moulding shrinkage, parallel	1.5 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.6 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	2300 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	55 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	6 %	ISO 527-1/-2
Tensile stress at break, 50mm/min	50 MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	40 %	ISO 527-1/-2
Flexural modulus	2280 MPa	ISO 178
Flexural stress at 3.5%	70 MPa	ISO 178
Charpy impact strength, 23°C	N kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	60 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	35 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.39 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10°C/min	280 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	100 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	160 °C	ISO 306
Vicat softening temperature, 50°C/h 10N	270 °C	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	80 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	95 E-6/K	ISO 11359-1/-2
Thermal conductivity, flow	0.319 <sup>[OT]</sup> W/(m K)	ISO 22007-2
Thermal conductivity, through plane	0.314 <sup>[OT]</sup> W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	1.7E-7 <sup>[OT]</sup> m <sup>2</sup> /s	ISO 22007-4
Effective thermal diffusivity, through plane	1.67E-7 <sup>[OT]</sup> m <sup>2</sup> /s	ISO 22007-4
Specific heat capacity of melt	1500 <sup>[OT]</sup> J/(kg K)	ISO 22007-4

[OT]: One time tested

### Flammability

Glow Wire Ignition Temperature, 0.75mm	850 °C	IEC 60695-2-13
--	--------	----------------

# FORTRON® FX55T1

Polyphenylene sulfide

## Physical/Other properties

Density	1250 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

## Injection

Drying Recommended	yes
Drying Temperature	130 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	330 °C
Min. melt temperature	310 °C
Max. melt temperature	340 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	120 °C
Min. mould temperature	80 °C
Max. mould temperature	160 °C
Hold pressure range	30 - 70 MPa
Back pressure	3.5 MPa

## Characteristics

Processing	Injection Moulding, Extrusion, Blow Moulding
Special characteristics	High impact or impact modified

## Additional information

Injection molding

### Processing

Drying – alternate 80°C, approx. 6 hours

Processing Notes

### Pre-Drying

Fortron® should in principle be predried. Because of the necessary low maximum residual moisture content, the use of dry air dryers is recommended. The dew point should be < -30°C. The time between drying and processing should be as short as possible.