

# SKX-9058 (PRELIMINARY)

PPS, 50% GF/MF reinforced, impact modified and heat shock resistant

Fortron SKX-9058 is a 50% glass-fiber and mineral reinforced grade with improved impact and heat shock resistance.

## Typical mechanical properties

Stress at break, 5mm/min	165 MPa	ISO 527-1/-2
Strain at break, 5mm/min	1.7 %	ISO 527-1/-2
Flexural Modulus	14500 MPa	ISO 178
Flexural Strength	252 MPa	ISO 178
Charpy impact strength, 23°C	50 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	10 kJ/m <sup>2</sup>	ISO 179/1eA

## Thermal properties

Melting temperature, 10°C/min	280 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	270 °C	ISO 75-1/-2

## Electrical properties

Comparative tracking index M	Group IIIa	IEC 60112
------------------------------	------------	-----------

## Other properties

Density	1670 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

## Injection

Drying Temperature	130 - 140 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Screw tangential speed	0.14 - 0.16 m/s
Max. mould temperature	140 - 160 °C

## Processing Texts

Pre-drying

Pre-drying conditions: Fortron should, in principle, be pre-dried. Because of the necessary low maximum residual moisture content, the use of dry air dryers is recommended. The dew point should be  $\leq -30$  deg. C. the time between drying and processing should be as short as possible.