

## FORFLEX® 7AI 00 D65 - SBS

### Description

Styrene Butadiene Compound - Transparent  
Injection Molding Grade

Physical properties	Value	Unit	Test Standard
Density	63.7	lb/ft <sup>3</sup>	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Shore D hardness-TPE, 3s	65		ISO 868

### Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	347 - 365	°F
Zone2 temperature	365 - 383	°F
Zone3 temperature	374 - 392	°F
Mold temperature	86 - 122	°F