

SOFPRENE® 510600A63 NEUTRO

Thermoplastic rubber compound
The data given on this TDS must be considered to be provisional

Typical mechanical properties

Stress at break	624 psi	ISO 527-1/-2 or ISO 37
Elongation at break	484 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	63	ISO 48-4 / ISO 868
Tear strength, normal	160 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------
