

SOFPRENE® 52129ZA88/SF NERO

SOFPRENE®

Product information

Resin Identification	SBS	ISO 1043
Part Marking Code	>SBS<	ISO 11469

Rheological properties

Melt mass-flow rate	77 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	5 kg	

Typical mechanical properties

Stress at break	5.4 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	500 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	88	ISO 48-4 / ISO 868
Tear strength, normal	34 kN/m	ISO 34-1

Physical/Other properties

Density	1030 kg/m ³	ISO 1183
---------	------------------------	----------