

SOFPRENE® 540200A70 NEUTRO

SOFPRENE®

Product information

Resin Identification	SBS	ISO 1043
Part Marking Code	>SBS<	ISO 11469

Typical mechanical properties

Tensile stress at 100% elongation	2.2 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	3 MPa	ISO 527-1/-2 or ISO 37
Stress at break	4.2 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	590 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	71	ISO 48-4 / ISO 868
Tear strength, normal	27 kN/m	ISO 34-1

Physical/Other properties

Density	1040 kg/m ³	ISO 1183
---------	------------------------	----------