

# SOFPRENE® 540298A90/P GRIGIO

## SOFPRENE®

### Product information

Resin Identification	SBS	ISO 1043
Part Marking Code	>SBS<	ISO 11469

### Rheological properties

Melt mass-flow rate	62 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	5 kg	

### Typical mechanical properties

Tensile stress at 100% elongation	4.7 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	5.6 MPa	ISO 527-1/-2 or ISO 37
Stress at break	6.4 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	450 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	92	ISO 48-4 / ISO 868
Tear strength, parallel	40 kN/m	ISO 34-1

### Physical/Other properties

Density	1040 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Characteristics

Processing	Injection Moulding
------------	--------------------