

# SOFPRENE® 540500A70 NEUTRO

## Typical mechanical properties

Stress at 100% elongation	334 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	464 psi	ISO 527-1/-2 or ISO 37
Stress at break	696 psi	ISO 527-1/-2 or ISO 37
Elongation at break	600 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	70	ISO 48-4 / ISO 868
Tear strength, normal	177 lb/in	ISO 34-1

## Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

## Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

---