

SOFPRENE® S227-65A

Compact, shiny, low cost, good for painting and spraying.

Typical mechanical properties

| | | |
|-----------------------|-----------|------------------------|
| Stress at break | 551 psi | ISO 527-1/-2 or ISO 37 |
| Elongation at break | 500 % | ISO 527-1/-2 or ISO 37 |
| Shore A hardness, 3s | 65 | ISO 48-4 / ISO 868 |
| Tear strength, normal | 143 lb/in | ISO 34-1 |

Other properties

| | | |
|---------|----------|----------|
| Density | 9 lb/gal | ISO 1183 |
|---------|----------|----------|

Additional information

Injection molding Please note that the suggested temperatures are estimations. The actual desired temperatures can vary based on the molding machine design.

Processing Texts

Longer pre-drying times/storage The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

Injection molding Please note that the suggested temperatures are estimations. The actual desired temperatures can vary based on the molding machine design.
