

**LAPRENE® 830000769/AB - SEBS**

Experimental Grade. Please contact your Celanese representative for further information.

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1160</b>	kg/m <sup>3</sup>	ISO 1183
<b>Mechanical properties (TPE)</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Shore A hardness, 3s	<b>67</b>	-	ISO 868
<b>Typical injection moulding processing conditions</b>			
<b>Temperature</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Zone1 temperature	<b>170</b>	°C	-
Zone2 temperature	<b>180</b>	°C	-
Zone3 temperature	<b>180</b>	°C	-
Zone4 temperature	<b>190</b>	°C	-
Mold temperature	<b>20 - 40</b>	°C	-