

**LAPRENE® 830000970 NEUTRO - SEBS**

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	56.1	lb/ft <sup>3</sup>	ISO 1183

<b>Mechanical properties (TPE)</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile stress at 100% strain	334	psi	ISO 37
Tensile stress at 300%, perpendicular	493	psi	ISO 37
Compression Set under constant strain at 70 °C, 24h	40	%	ISO 815
Tensile strain at break (TPE)	832	%	ISO 37
Tensile stress at break (TPE)	2200	psi	ISO 37
Shore A hardness-TPE, 3s	73	-	ISO 868
Tear strength	246	lb/in	ISO 34-1
Tensile set (elastomers)	10	%	ASTM D412

**Typical injection moulding processing conditions**

<b>Temperature</b>	<b>Value</b>	<b>Unit</b>
Zone1 temperature	329 - 347	°F
Zone2 temperature	347 - 365	°F
Zone3 temperature	356 - 374	°F
Nozzle temperature	365 - 383	°F
Mold temperature	68 - 104	°F

**Other text information**

**Pre-drying**

Drying not necessary

**Longer pre-drying times/storage**

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.