

LAPRENE® 83F901550 NERO

Typical mechanical properties

Stress at 100% elongation	1.1 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1.7 MPa	ISO 527-1/-2 or ISO 37
Stress at break	6.2 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	880 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	49	ISO 48-4 / ISO 868
Compression set at 70°C, 24h	41 %	ISO 815
Tensile set	8.6 %	ISO 2285
Tear strength, normal	19 kN/m	ISO 34-1

Other properties

Density	1040 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

Processing Texts

Pre-drying	Drying not necessary
Longer pre-drying times/storage	Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.