

LAPRENE® 83FE00865 NEUTRO - SEBS

Physical properties	Value	Unit	Test Standard
Density	56.2	lb/ft ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	145	psi	ISO 37
Tensile stress at 300%, perpendicular	218	psi	ISO 37
Tensile strain at break (TPE)	700	%	ISO 37
Tensile stress at break (TPE)	2780	psi	ISO 37
Shore A hardness-TPE, 3s	56	-	ISO 868
Tear strength	263	lb/in	ISO 34-1

Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	320 - 338	°F
Zone2 temperature	338 - 356	°F
Zone3 temperature	347 - 365	°F
Nozzle temperature	329 - 347	°F
Mold temperature	68 - 104	°F

Typical extrusion processing conditions

Temperature	Value	Unit
Zone 1 temperature	320 - 338	°F
Zone 2 temperature	338 - 356	°F
Zone 3 temperature	347 - 365	°F
Die head temperature	347 - 365	°F

Other text information

Pre-drying

Drying not necessary

Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.