

# LAPRENE® 8E0..A65

## Typical mechanical properties

Stress at 100% elongation	1.8 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	2.7 MPa	ISO 527-1/-2 or ISO 37
Stress at break	7.8 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	731 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	66	ISO 48-4 / ISO 868
Tear strength, normal	31 kN/m	ISO 34-1

## Other properties

Density	1100 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

## Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

## Processing Texts

Longer pre-drying times/storage      The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

---