

LAPRENE® 8EC..A75

Typical mechanical properties

Stress at 100% elongation	305 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	493 psi	ISO 527-1/-2 or ISO 37
Stress at break	986 psi	ISO 527-1/-2 or ISO 37
Elongation at break	617 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	76	ISO 48-4 / ISO 868
Tear strength, normal	183 lb/in	ISO 34-1

Other properties

Density	10 lb/gal	ISO 1183
---------	-----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
