

LAPRENE® 8EC5..A50

Typical mechanical properties

Stress at break	711 psi	ISO 527-1/-2 or ISO 37
Elongation at break	620 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	51	ISO 48-4 / ISO 868
Tear strength, normal	120 lb/in	ISO 34-1

Other properties

Density	10 lb/gal	ISO 1183
---------	-----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage

The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Ford	WSS-M2D505-4A7	Black