

LAPRENE® 8K1000A90/F NEUTRO

Typical mechanical properties

Stress at 100% elongation	740 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1410 psi	ISO 527-1/-2 or ISO 37
Stress at break	2780 psi	ISO 527-1/-2 or ISO 37
Elongation at break	520 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	87	ISO 48-4 / ISO 868
Tear strength, normal	394 lb/in	ISO 34-1

Other properties

Density	9 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	86 - 122 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
