

LAPRENE® 8K5901A60 NERO

LAPRENE®

Product information

| | | |
|----------------------|--------|-----------|
| Resin Identification | SEBS | ISO 1043 |
| Part Marking Code | >SEBS< | ISO 11469 |

Rheological properties

| | | |
|----------------------------------|------------|----------|
| Melt mass-flow rate | 12 g/10min | ISO 1133 |
| Melt mass-flow rate, Temperature | 190 °C | |
| Melt mass-flow rate, Load | 5 kg | |

Typical mechanical properties

| | | |
|------------------------------------|----------|------------------------|
| Tensile stress at 100% elongation | 2.4 MPa | ISO 527-1/-2 or ISO 37 |
| Stress at 300% elongation | 5 MPa | ISO 527-1/-2 or ISO 37 |
| Stress at break | 12.4 MPa | ISO 527-1/-2 or ISO 37 |
| Elongation at break, perpendicular | 570 % | ISO 527-1/-2 or ISO 37 |
| Shore A hardness, 3s | 63 | ISO 48-4 / ISO 868 |
| Tear strength, normal | 40 kN/m | ISO 34-1 |

Physical/Other properties

| | | |
|---------|------------------------|----------|
| Density | 1050 kg/m ³ | ISO 1183 |
|---------|------------------------|----------|

Injection

| | |
|---------------------------------|---------|
| Drying Recommended | yes |
| Drying Temperature | 80 °C |
| Drying Time, Dehumidified Dryer | 2 h |
| Melt Temperature Optimum | 180 °C |
| Min. melt temperature | 170 °C |
| Max. melt temperature | 190 °C |
| Screw tangential speed | ≤15 m/s |
| Mold Temperature Optimum | 30 °C |
| Min. mould temperature | 20 °C |
| Max. mould temperature | 40 °C |

Characteristics

| | |
|------------|--------------------|
| Processing | Injection Moulding |
|------------|--------------------|

Additional information

Processing Notes

Pre-Drying

2h@80C

Storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.