

LAPRENE® 8K6000A60 NEUTRO - SEBS

Physical properties	Value	Unit	Test Standard
Density	64.2	lb/ft ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	319	psi	ISO 37
Tensile stress at 300%, perpendicular	566	psi	ISO 37
Tensile strain at break (TPE)	590	%	ISO 37
Tensile stress at break (TPE)	1490	psi	ISO 37
Shore A hardness-TPE, 3s	65	-	ISO 868
Tear strength	194	lb/in	ISO 34-1
Tensile set (elastomers)	6	%	ASTM D412

Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	401 - 419	°F
Zone2 temperature	419 - 437	°F
Zone3 temperature	437 - 455	°F
Nozzle temperature	437 - 455	°F
Mold temperature	86 - 122	°F

Typical extrusion processing conditions

Temperature	Value	Unit
Zone 1 temperature	401 - 419	°F
Zone 2 temperature	419 - 437	°F
Zone 3 temperature	437 - 455	°F
Die head temperature	437 - 455	°F

Other text information
Pre-drying

2h@80C

Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.