

LAPRENE® 8K8200A55 NEUTRO

Typical mechanical properties

Stress at 100% elongation	247 psi	ISO 527-1/-2 or ISO 37
Stress at break	1450 psi	ISO 527-1/-2 or ISO 37
Elongation at break	>300 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	51	ISO 48-4 / ISO 868
Tear strength, normal	171 lb/in	ISO 34-1

Other properties

Density	10 lb/gal	ISO 1183
---------	-----------	----------

Injection

Max. mould temperature	95 - 122 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
