

# LAPRENE® 8M0..A25

## Note:

Agglomeration of low hardness Laprene grades (below 35 Shore A) typically occurs and is characterized by pellet “blocking” behavior. Agglomeration does not influence material properties or part performance. It is recommended to avoid stacking pallets to reduce the tendency of agglomeration.

## Typical mechanical properties

Shore A hardness, 3s	25	ISO 48-4 / ISO 868
----------------------	----	--------------------

## Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

## Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

## Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--