

LAPRENE® 8M0..A75

Typical mechanical properties

Stress at 100% elongation	406 psi	ISO 527-1/-2 or ISO 37
Stress at break	1580 psi	ISO 527-1/-2 or ISO 37
Elongation at break	745 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	77	ISO 48-4 / ISO 868
Tear strength, normal	229 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage

The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Stellantis - Chrysler	CPN 4453	Black (Campo Bom)