

# LAPRENE® 8M3..A70

## Typical mechanical properties

Stress at 100% elongation	334 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	493 psi	ISO 527-1/-2 or ISO 37
Stress at break	1480 psi	ISO 527-1/-2 or ISO 37
Elongation at break	763 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	71	ISO 48-4 / ISO 868
Tear strength, normal	206 lb/in	ISO 34-1

## Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

## Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

## Processing Texts

Longer pre-drying times/storage      The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

---