

# LAPRENE® 8M35P..A75

## Typical mechanical properties

Stress at break	1540 psi	ISO 527-1/-2 or ISO 37
Elongation at break	720 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	75	ISO 48-4 / ISO 868

## Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

## Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

## Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--