

LAPRENE® 8M3X5901A75

Typical mechanical properties

Stress at break	522 psi	ISO 527-1/-2 or ISO 37
Elongation at break	300 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	75	ISO 48-4 / ISO 868
Tear strength, normal	149 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 122 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage

The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.