

LAPRENE® 8MF..D40

Typical mechanical properties

Stress at 100% elongation	1020 psi	ISO 527-1/-2 or ISO 37
Stress at break	2640 psi	ISO 527-1/-2 or ISO 37
Elongation at break	711 %	ISO 527-1/-2 or ISO 37
Tear strength, normal	371 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
