

LAPRENE® 8MG..A10

Note:

Agglomeration of very low hardness Laprene grades (below 15 Shore A) typically occurs and is characterized by pellet “blocking” behavior. Agglomeration does not influence material properties or part performance. It is recommended to avoid stacking pallets or more than 3 individual bags to reduce the tendency of agglomeration.

Typical mechanical properties

Shore A hardness, 3s	7	ISO 48-4 / ISO 868
----------------------	---	--------------------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--