

LAPRENE® 8ML35 001 A60

Typical mechanical properties

Stress at break	1020 psi	ISO 527-1/-2 or ISO 37
Elongation at break	720 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	60	ISO 48-4 / ISO 868

Other properties

Density	9 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
