

LAPRENE® 8P0901A60 NERO - SEBS

Physical properties	Value	Unit	Test Standard
Density	58.9	lb/ft ³	ISO 1183
Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	305	psi	ISO 37
Tensile stress at 300%, perpendicular	696	psi	ISO 37
Compression Set under constant strain at 70 °C, 24h	27	%	ISO 815
Compression Set under constant strain at 100 °C, 24h	42	%	ISO 815
Tensile strain at break (TPE)	519	%	ISO 37
Tensile stress at break (TPE)	1170	psi	ISO 37
Shore A hardness-TPE, 3s	62	-	ISO 868
Tear strength	149	lb/in	ISO 34-1

Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	419 - 437	°F
Zone2 temperature	437 - 455	°F
Zone3 temperature	446 - 464	°F
Nozzle temperature	446 - 464	°F
Mold temperature	86 - 122	°F

Other text information
Pre-drying

Drying not necessary

Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.