

LAPRENE® L848-60A

Typical mechanical properties

Stress at break	435 psi	ISO 527-1/-2 or ISO 37
Elongation at break	500 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	60	ISO 48-4 / ISO 868

Other properties

Density	10 lb/gal	ISO 1183
---------	-----------	----------

Processing Texts

Longer pre-drying times/storage The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
