

---

**LAPRENE® NERO 83E200A60/CB - SEBS**

---

**Mechanical properties (TPE)**

	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Shore A hardness, 3s	<b>62</b>	-	ISO 868

**Typical injection moulding processing conditions**

<b>Temperature</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Zone1 temperature	<b>160 - 170</b>	°C	-
Zone2 temperature	<b>170 - 180</b>	°C	-
Zone3 temperature	<b>175 - 185</b>	°C	-
Nozzle temperature	<b>165 - 175</b>	°C	-
Extrusion Molding, Head Temperature	<b>180 - 190</b>	°C	Internal

**Other text information**

---

**Pre-drying**

Drying not necessary

**Longer pre-drying times/storage**

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.