

## LAPRENE® NERO 8P1901A60 - SEBS

Physical properties	Value	Unit	Test Standard
Density	1130	kg/m <sup>3</sup>	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	1.9	MPa	ISO 37
Tensile stress at 300% strain	4.5	MPa	ISO 37
Tensile strain at break (TPE)	660	%	ISO 37
Tensile stress at break (TPE)	8.1	MPa	ISO 37
Shore A hardness, 3s	64	-	ISO 868
Tear strength	31	kN/m	ISO 34-1

### Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	215 - 225	°C	-
Zone2 temperature	225 - 235	°C	-
Zone3 temperature	230 - 240	°C	-
Nozzle temperature	230 - 240	°C	-
Mold temperature	30 - 50	°C	-

### Other text information

#### Pre-drying

Drying not necessary

#### Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.