

---

**SOFPRENE® 238VZ9345 VERDE - SEBS**

---

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1000</b>	kg/m <sup>3</sup>	ISO 1183

<b>Mechanical properties (TPE)</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile strain at break (TPE)	<b>450</b>	%	ISO 37
Tensile stress at break (TPE)	<b>2</b>	MPa	ISO 37
Shore A hardness, 3s	<b>45</b>	-	ISO 868
Tear strength	<b>13</b>	kN/m	ISO 34-1
Abrasion resistance	<b>500</b>	mm <sup>3</sup>	ISO 4649

**Typical injection moulding processing conditions**

---

<b>Temperature</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Zone1 temperature	<b>155 - 165</b>	°C	-
Zone2 temperature	<b>175 - 185</b>	°C	-