

## PIBIFLEX® 56X01 - TPC

### Description

PIBIFLEX® 56X01 is a nominal 60 Shore D thermoplastic polyester elastomer for injection molding applications and use as a performance modifier for TPE compounding.

### Physical properties

ISO	Value	Unit	Test Standard
Density	1190	kg/m <sup>3</sup>	ISO 1183

### Mechanical properties

ISO	Value	Unit	Test Standard
Tensile stress at break, 50mm/min	33	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	>350	%	ISO 527-2/1A
Flexural modulus, 23°C	109	MPa	ISO 178
Shore D hardness, 15s	60	-	ISO 868

### Thermal properties

ISO	Value	Unit	Test Standard
Melting temperature, 10°C/min	201	°C	ISO 11357-1/-3

### Typical injection moulding processing conditions

#### Pre Drying

	LowMaxRes	DryTime	DryTemp
max	0.05 %	4 h	110 °C
min			100 °C