

RITEFLEX® RKX-150 - TPC

Experimental Grade. Please contact your Celanese representative for further information.

| Physical properties | Value | Unit | Test Standard |
|----------------------------|--------------|-------------|----------------------|
| Melt flow rate, MFR | 30 | g/10min | ISO 1133 |
| MFR temperature | 220 | °C | ISO 1133 |
| MFR load | 2.16 | kg | ISO 1133 |
| Water absorption, 23°C-sat | 0.5 | % | ISO 62 |

| Mechanical properties | Value | Unit | Test Standard |
|--------------------------------------|--------------|-------------------|----------------------|
| Flexural modulus, 23°C | 82 | MPa | ISO 178 |
| Flexural stress at 3.5% strain | 3 | MPa | ISO 178 |
| Charpy notched impact strength, 23°C | 28 | kJ/m ² | ISO 179/1eA |

Characteristics**Product Categories**

Unfilled