

# FORFLEX® 710002A90 NEUTRO

## Rheological properties

Melt mass-flow rate	3 g/10min	ISO 1133
Melt mass-flow rate, Temperature	200 °C	
Melt mass-flow rate, Load	5 kg	

## Typical mechanical properties

Stress at 100% elongation	6.1 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	6.8 MPa	ISO 527-1/-2 or ISO 37
Stress at break	11.7 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	730 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	94	ISO 48-4 / ISO 868
Tear strength, normal	68 kN/m	ISO 34-1

## Other properties

Density	960 kg/m <sup>3</sup>	ISO 1183
---------	-----------------------	----------

---