HK:+852-69575415 China GuangDong:+13538586433 ShangHai:+18816996168

Celanese
The chemistry inside innovation™

FORFLEX® 7AI 00 D65

Styrene Butadiene Compound - Transparent
Injection Molding Grade

Rheological properties

Melt mass-flow rate	11	g/10min	ISO 1133
Melt mass-flow rate, Temperature	200	°C	
Melt mass-flow rate, Load	5	kg	

Other properties

Density	1020	kg/m³	ISO 1183

Injection

Max. mould temperature	30 - 50	°C

Processing Texts

Pre-drying	Dyryng is not typically required
Longer pre-drying times/storage	The product should be stored in a covered facility away from moisture and heat.