

# FORFLEX® TPT 033 BC BLUE

## FORFLEX®

Styrene Butadiene Compound - Transparent  
Injection Molding Grade

### Product information

Resin Identification	TPO	ISO 1043
Part Marking Code	>TPO<	ISO 11469

### Rheological properties

Melt mass-flow rate	10 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	2.16 kg	

### Typical mechanical properties

Shore A hardness, 3s	92	ISO 48-4 / ISO 868
----------------------	----	--------------------

### Physical/Other properties

Density	930 kg/m <sup>3</sup>	ISO 1183
---------	-----------------------	----------

### Additional information

Processing Notes

#### Pre-Drying

Drying is not typically required

#### Storage

The product should be stored in a covered facility away from moisture and heat.