

# FORPRENE® 65VS01A65

## Typical mechanical properties

Stress at 100% elongation	334 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	464 psi	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	66	ISO 48-4 / ISO 868

## Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

## Injection

Max. mold temperature	68 - 104 °F
-----------------------	-------------

## Processing Texts

Longer pre-drying times/storage Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.