

FORPRENE® 6B0901A83

Typical mechanical properties

Stress at 100% elongation	595 psi	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	83	ISO 48-4 / ISO 868

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Processing Texts

Longer pre-drying times/storage Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.