

FORPRENE® 6E0901A45

Typical mechanical properties

Stress at 100% elongation	203 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	348 psi	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	46	ISO 48-4 / ISO 868
Tensile set	8 %	ISO 2285

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.