

# FORPRENE® 6E5901A80

## Typical mechanical properties

Stress at 100% elongation	566 psi	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	82	ISO 48-4 / ISO 868
Tensile set	23 %	ISO 2285

## Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

## Processing Texts

Longer pre-drying times/storage Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

---