

## FORPRENE® 6ZB901A90 NERO - TPV

Physical properties	Value	Unit	Test Standard
Density	61.7	lb/ft <sup>3</sup>	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100%, perpendicular	899	psi	ISO 37
Tensile stress at 300%, perpendicular	1100	psi	ISO 37
Compression set, 70 °C, 22h, Type A	58	%	ISO 815
Tensile strain at break, perpendicular	616	%	ISO 37
Tensile stress at break, perpendicular	1830	psi	ISO 37
Shore A hardness-TPE, 15s	93	-	ISO 868
Tear strength, Method Ba, perpendicular	349	lb/in	ISO 34-1
Tensile set (elastomers)	30	%	ASTM D412

### Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	329 - 347	°F
Zone2 temperature	347 - 365	°F
Zone3 temperature	356 - 374	°F
Nozzle temperature	374 - 392	°F
Mold temperature	356 - 374	°F

### Other text information

#### Pre-drying

3h@80C

#### Longer pre-drying times/storage

Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

### Characteristics

**Processing**                      Blow molding