

## FORPRENE® 6ZB901D40 NERO - TPV

Physical properties	Value	Unit	Test Standard
Density	61	lb/ft <sup>3</sup>	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100%, perpendicular	1250	psi	ISO 37
Tensile stress at 300%, perpendicular	1410	psi	ISO 37
Tensile strain at break, perpendicular	620	%	ISO 37
Tensile stress at break, perpendicular	2420	psi	ISO 37
Shore D hardness-TPE, 15s	42	-	ISO 868
Tear strength, Method Ba, perpendicular	394	lb/in	ISO 34-1

### Typical injection moulding processing conditions

Temperature	Value	Unit
Zone1 temperature	329 - 347	°F
Zone2 temperature	347 - 365	°F
Zone3 temperature	356 - 374	°F
Nozzle temperature	374 - 392	°F
Mold temperature	356 - 374	°F

### Other text information

#### Pre-drying

3h@80C

#### Longer pre-drying times/storage

Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

### Characteristics

**Processing**                      Blow molding