

---

**FORPRENE® GRIGIO 6MD4D3A85 - TPV**

---

Physical properties	Value	Unit	Test Standard
Density	958	kg/m <sup>3</sup>	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	5	MPa	ISO 37
Tensile stress at 300% strain	6.6	MPa	ISO 37
Tensile strain at break (TPE)	518	%	ISO 37
Tensile stress at break (TPE)	10	MPa	ISO 37
Shore A hardness, 15s	90	-	ISO 868
Tear strength	50	kN/m	ISO 34-1

**Typical injection moulding processing conditions**

Temperature	Value	Unit	Test Standard
Zone1 temperature	175 - 185	°C	-
Zone2 temperature	185 - 195	°C	-
Zone3 temperature	190 - 200	°C	-
Nozzle temperature	195 - 205	°C	-
Mold temperature	20 - 40	°C	-

**Other text information**

---

**Pre-drying**

---

3h@80C

**Longer pre-drying times/storage**

---

Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.