

---

**FORPRENE® NERO 6M5901A50 - TPV**


---

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1000	kg/m <sup>3</sup>	ISO 1183

<b>Mechanical properties (TPE)</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile stress at 100% strain	1.6	MPa	ISO 37
Tensile stress at 300% strain	2.5	MPa	ISO 37
Tensile strain at break (TPE)	627	%	ISO 37
Tensile stress at break (TPE)	4.8	MPa	ISO 37
Shore A hardness, 15s	52	-	ISO 868
Tear strength	20	kN/m	ISO 34-1

---

**Typical injection moulding processing conditions**


---

<b>Temperature</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Zone1 temperature	155 - 165	°C	-
Zone2 temperature	165 - 175	°C	-
Zone3 temperature	175 - 185	°C	-
Nozzle temperature	180 - 190	°C	-
Mold temperature	20 - 40	°C	-

---

**Other text information**


---



---

**Pre-drying**


---

3h@80C

---

**Longer pre-drying times/storage**


---

Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.