

---

**FORPRENE® NEUTRO 6M0001A45 - TPV**


---

| Physical properties | Value | Unit              | Test Standard |
|---------------------|-------|-------------------|---------------|
| Density             | 991   | kg/m <sup>3</sup> | ISO 1183      |

| Mechanical properties (TPE)   | Value | Unit | Test Standard |
|-------------------------------|-------|------|---------------|
| Tensile stress at 100% strain | 1.5   | MPa  | ISO 37        |
| Tensile stress at 300% strain | 2.5   | MPa  | ISO 37        |
| Tensile strain at break (TPE) | 567   | %    | ISO 37        |
| Tensile stress at break (TPE) | 4.4   | MPa  | ISO 37        |
| Shore A hardness, 15s         | 47    | -    | ISO 868       |
| Tear strength                 | 18    | kN/m | ISO 34-1      |

---

**Typical injection moulding processing conditions**


---

| Temperature        | Value     | Unit | Test Standard |
|--------------------|-----------|------|---------------|
| Zone1 temperature  | 155 - 165 | °C   | -             |
| Zone2 temperature  | 165 - 175 | °C   | -             |
| Zone3 temperature  | 175 - 185 | °C   | -             |
| Nozzle temperature | 180 - 190 | °C   | -             |
| Mold temperature   | 20 - 40   | °C   | -             |

---

**Other text information**


---



---

**Pre-drying**


---

3h@80C

---

**Longer pre-drying times/storage**


---

Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.