

SANTOPRENE® 121-67W175

SANTOPRENE®

A soft, black, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance, and is designed for thin wall or complex profile extrusion applications. This grade of Santoprene® TPV is shear-dependent and can be processed on conventional thermoplastics equipment for extrusion, thermoforming or vacuum forming. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Recommended for applications requiring excellent flex fatigue resistance
- Excellent ozone resistance
- Designed for improved UV resistance
- Designed for extruding thin wall sections with excellent definition (down to 0.33 mm [0.013"] radius) and to maximize run length with minimal build-up of material on screen packs or narrow sections of dies

Product information

Resin Identification	TPV	ISO 1043
Part Marking Code	>TPV<	ISO 11469

Typical mechanical properties

Tensile stress at 100% elongation, perpendicular	2.89 MPa	ISO 37
Tensile stress at break, perpendicular	6.83 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	432 %	ISO 527-1/-2 or ISO 37
Brittleness Temperature	-59 °C	ASTM D 746
Low temperature brittleness	-59 °C	ISO 812
Shore A hardness, 15s	72	ISO 48-4 / ISO 868
Compression set, 70 °C, 24h	29 %	ISO 815
Compression set, 125 °C, 70h	43 %	ISO 815
Tear strength, normal	24 kN/m	ISO 34-1

Specific Application Suitability

Continuous Upper Temperature Resistance, 1000h	135 °C	SAE J2236
--	--------	-----------

Flammability

FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 2 mm	25.9 mm/min	ISO 3795 (FMVSS 302)

Electrical properties

Relative permittivity, 60Hz	2.6	IEC 62631-2-1
-----------------------------	-----	---------------

Physical/Other properties

Density	970 kg/m ³	ISO 1183
---------	-----------------------	----------

SANTOPRENE® 121-67W175

SANTOPRENE®

Extrusion

Drying Temperature	82 °C
Drying Time, Dehumidified Dryer	3 h
Melt Temperature Range	177 - 204 °C

Characteristics

Processing	Extrusion, Sheet Extrusion, Coextrusion, Thermoforming
Delivery form	Pellets
Special characteristics	U.V. stabilised or stable to weather

Additional information

Non Standard Data

Property Name	Condition	Value	Unit	Standard
Change in Tensile Strength	150 °C, 168h	-12.1	%	ISO 188
Change in Tensile Strain at Break	150 °C, 168h	-0.5	%	ISO 188
Change in Shore A Hardness	150 °C, 168h	0	-	ISO 188

Injection molding

Holding pressure should be about 50 to 75% of the actual injection pressure. A high screw RPM (100 to 200) is recommended. Back pressure is not always needed, however, a back pressure of 0.3 to 0.7 MPa may be used to ensure a homogeneous melt and maintain a consistent shot size. A higher back pressure is normally employed when using masterbatches.

Processing Notes

Processing Notes

Desiccant drying for 3 hours at 80 °C (180 °F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230 °C (350 to 450 °F) and is incompatible with acetal and PVC. Do not exceed 15% drawdown.

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Chery	Q/SQR.04.1195-2011	
Ford	WSS-M2D379-B1	
GAC	QJ/GAC 1240.022	

SANTOPRENE® 121-67W175

SANTOPRENE®

Geely	Q/JLY J7110166C-2024	
General Motors	GMW15812P-TPV(EPDM+PP)-Type 5E	N/A
Li Auto	Q/LiA5310057	2021 (V2)
Mercedes-Benz	DBL5562	
Renault	FRM 18-27-040 /--B, No Spec, Special Part Approval, See Your CE Account Manager.	
SAIC Motor	SMTC 5 320 024	
Stellantis	55248_02 EMP70	01378_22_03405;MS-AR-100 BGV
VW Group	TL 526 41C	
VW Group	VW 50123	
VW Group	VW 52703	
VW Group	VW TL 527 03	