

SANTOPRENE® 8221-65M300

SANTOPRENE®

A soft, colorable, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is designed for automotive interior applications requiring low fogging and good appearance. This grade of Santoprene™ TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Neutral, easy coloring formulation.
- Excellent ozone resistance.
- Used in sealing applications.
- Recommended for applications requiring excellent flex fatigue resistance.
- Designed for improved UV resistance.

Product information

| | | |
|----------------------|-------|-----------|
| Resin Identification | TPV | ISO 1043 |
| Part Marking Code | >TPV< | ISO 11469 |

Typical mechanical properties

| | | |
|--------------------------------------------------|---------|------------------------|
| Tensile stress at 100% elongation, perpendicular | 2.1 MPa | ISO 37 |
| Tensile stress at break, perpendicular | 4.7 MPa | ISO 527-1/-2 or ISO 37 |
| Elongation at break, perpendicular | 470 % | ISO 527-1/-2 or ISO 37 |
| Brittleness Temperature | -60 °C | ASTM D 746 |
| Low temperature brittleness | -60 °C | ISO 812 |
| Shore A hardness, 15s | 65 | ISO 48-4 / ISO 868 |

Flammability

| | | |
|------------------------------|-------------|----------------------|
| FMVSS Class | B | ISO 3795 (FMVSS 302) |
| Burning rate, Thickness 2 mm | 23.2 mm/min | ISO 3795 (FMVSS 302) |

Physical/Other properties

| | | |
|---------|-----------------------|----------|
| Density | 920 kg/m ³ | ISO 1183 |
|---------|-----------------------|----------|

Injection

| | |
|---------------------------------|---------|
| Drying Recommended | yes |
| Drying Temperature | 80 °C |
| Drying Time, Dehumidified Dryer | ≥3 h |
| Processing Moisture Content | ≤0.08 % |
| Melt Temperature Optimum | 200 °C |
| Min. melt temperature | 185 °C |
| Max. melt temperature | 215 °C |
| Mold Temperature Optimum | 35 °C |
| Min. mould temperature | 20 °C |
| Max. mould temperature | 50 °C |

SANTOPRENE® 8221-65M300

SANTOPRENE®

Characteristics

| | |
|-------------------------|-------------------------------------------------|
| Processing | Injection Moulding, Multi Injection Moulding |
| Delivery form | Pellets |
| Special characteristics | U.V. stabilised or stable to weather, High Flow |

Additional information

| | |
|-------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Injection molding | Holding pressure should be about 50 to 75% of the actual injection pressure. A high screw RPM (100 to 200) is recommended. Back pressure is not always needed, however, a back pressure of 0.3 to 0.7 MPa may be used to ensure a homogeneous melt and maintain a consistent shot size. A higher back pressure is normally employed when using masterbatches. |
|-------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

Processing Notes

Processing Notes

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC.

Santoprene® TPV has a relatively high melt viscosity at low shear rates. Viscosity decreases as the shear rate increases.
Increasing temperature has little effect on TPV melt viscosity. Smaller gates and higher shear rates keep melt viscosity low and improve melt flow. Please also refer to the injection molding guide.

Automotive

| OEM | STANDARD | ADDITIONAL INFORMATION |
|-----------------------|--------------------------------------|-------------------------------------------------|
| Ford | WSS-M2D510-A6 | |
| General Motors | GMW15816P-TPV-EPDM+PP-Class-I-Type-5 | Non-phenolic cured |
| Mercedes-Benz | DBL5562-30 | SANTOPRENE8221-65M300_DBL5562-30_2022-04-01.pdf |
| Mercedes-Benz | STD4376-7 | Santoprene8221-65M300_STD4376-7_2023-09-13.pdf |
| Stellantis - Chrysler | MS-AR-100 BMV2-HF | Natural |
| VW Group | VW 50123 | SANTOPRENE8221-65M300_VW50123_2022-04-01.pdf |
| VW Group | VW 50180 | SANTOPRENE8221-65M300_VW50180_2022-04-01.pdf |